VALIANT: Providing Constant, Safe and Reliable Power



VRLA AGM SEALED LEAD ACID Battery

VTA12-55/12V61Ah

The Valiant VTA series AGM batteries are designed for float and cycling applications. The VTA series offers a 30% higher cycle life than standard AGM and a 10-year float life that is achieved through a slightly different active paste material and a slightly stronger electrolyte. They are perfectly suited for UPS/ Telecom, remote site, and emergency power systems.









GENERAL FEATURES

- 30% more cycle life
- Deep discharge recovery, 700 cycles @ 50% DOD
- Thick plate design with high tin/low calcium alloy
- 10-year service life in float applications
- High power density

APPLICATIONS


- Telecom, controls, remote site
- UPS and inverter systems
- Solar and wind systems
- Emergency backup power systems
- RV and marine

COMPLIED STANDARDS



DIMENSIONS & WEIGHT

Length(mm/inch)	229/9.02
Width(mm/inch)	138/5.43
Height(mm/inch)	208/8.19
Total Height(mm/inch)	212/8.35
Weight(kg/lbs)(\pm 3%)	16.2/35.7



TECHNICAL SPECIFICATIONS

No	12V(6 cells per unit)				
Design l	10 Years				
Nominal Capacity @2	25°C(10 hour ra	ate@5.50A,10.8V)	55Ah		
	20houi	rate (3.05A,10.8V)	61Ah		
Capacity @25°C	5 hour	rate (10.0A,10.5V)	50Ah		
	1 hou	r rate (36.6A,9.6V)	36.6Ah		
Internal Resistance	Full Charge	d Battery@25°C	≤8.2mΩ		
		Discharge	-15℃~45℃		
Ambient Temperature		Charge	-15℃~45℃		
		Storage	-15℃~45℃		
Max.Disc	Max.Discharge Current@25°C				
C	40 ℃		105%		
Capacity affected by		25℃	100%		
Temperature		$0^{\circ}\mathbb{C}$	85%		
(10 hour)		-15℃	65%		
Self-Disch	arge@25°C per	r Month	3%		
C4	41 1 1	Initial Charging Curi	ent Less than 13.8A		

Standby Use Charge (Constant Voltage 13.6-13.8V Voltage) @25°C Initial Charging Current Less than 13.8A Cycle Use Voltage 14.4-14.9V

BATTERY DISCHARGE **TABEL**

Discharge Constant Current per Cell (Amperes at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	92.9	57.8	41.5	36.6	22.3	16.3	10.5	6.4	5.72	3.17
1.65V	89.0	56.2	40.3	35.6	21.9	16.0	10.3	6.3	5.67	3.14
1.70V	85.1	54.7	39.2	34.6	21.5	15.7	10.2	6.3	5.61	3.11
1.75V	81.3	53.1	38.1	33.7	21.0	15.3	10.0	6.2	5.56	3.08
1.80V	77.4	51.6	37.0	32.7	20.5	15.0	9.9	6.2	5.50	3.05

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	173.2	107.8	77.3	68.2	41.6	30.4	19.6	11.9	10.7	5.9
1.65V	166.0	104.9	75.2	66.4	40.8	29.9	19.3	11.8	10.6	5.9
1.70V	158.8	102.0	73.2	64.6	40.1	29.3	19.0	11.7	10.5	5.8
1.75V	151.5	99.1	71.1	62.8	39.1	28.6	18.7	11.6	10.4	5.7
1.80V	144.3	96.2	69.0	60.9	38.2	27.9	18.5	11.5	10.3	5.7


Note: The above data is based on average values and can typically be achieved within 3 charge/discharge cycles. Battery designs and specifications are subject to change without notice. Contact Valiant for the latest information.





VRLA AGM SEALED LEAD ACID Battery


VTA12-55/12V61Ah


PERFORMANCE CHARACTERISTICS














BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container &Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	Fire resistance ABS (UL94-V0)	Flame Si-Rubber and aging resistance	Female Copper Insert M6	Advanced AGM separator for high pressure cell design	Dilute high purity sulfuric acid	Two layers epoxy resin seal

